

JANTZEN AUDIO

Cross Coils - Foil Inductors

Sorted by AWG / Inductance (mH)

Sizing: OD (outer diameter) x H (height)

Index:	Description:	Weight (kg):
000-7000-08-0039	Cross Coil 0,390mH +/-2% 0,044Ω +/-5% 8AWG OD86 H55	1,795
000-7000-08-0056	Cross Coil 0,560mH +/-2% 0,057Ω +/-5% 8AWG OD93 H55	2,200
000-7000-08-0068	Cross Coil 0,680mH +/-2% 0,064Ω +/-5% 8AWG OD99 H55	2,470
000-7000-08-0220	Cross Coil 2,200mH +/-2% 0,13Ω +/-5% 8AWG OD136 H55	4,720
000-7000-08-0390	Cross Coil 3,900mH +/-2% 0,18Ω +/-5% 8AWG OD158 H55	6,600
000-7001	Cross Coil 0,010mH +/-2% 0,02Ω +/-5% 12AWG OD32 H55	0,113
000-7002	Cross Coil 0,020mH +/-2% 0,02Ω +/-5% 12AWG OD34 H55	0,168
000-7004	Cross Coil 0,050mH +/-2% 0,04Ω +/-5% 12AWG OD39 H55	0,224
000-7005	Cross Coil 0,080mH +/-2% 0,05Ω +/-5% 12AWG OD43 H55	0,284
000-70056	Cross Coil 0,086mH +/-2% 0,05Ω +/-5% 12AWG OD43 H55	0,289
000-7009	Cross Coil 0,100mH +/-2% 0,05Ω +/-5% 12AWG OD45 H55	0,320
000-7010	Cross Coil 0,110mH +/-2% 0,05Ω +/-5% 12AWG OD45 H55	0,341
000-7011	Cross Coil 0,120mH +/-2% 0,06Ω +/-5% 12AWG OD46 H55	0,343
000-7015	Cross Coil 0,150mH +/-2% 0,07Ω +/-5% 12AWG OD47 H55	0,384
000-7016	Cross Coil 0,160mH +/-2% 0,07Ω +/-5% 12AWG OD49 H55	0,404
000-7018	Cross Coil 0,180mH +/-2% 0,07Ω +/-5% 12AWG OD50 H55	0,430
000-7019	Cross Coil 0,190mH +/-2% 0,07Ω +/-5% 12AWG OD51 H55	0,443
000-7020	Cross Coil 0,200mH +/-2% 0,08Ω +/-5% 12AWG OD51 H55	0,443
000-7025	Cross Coil 0,220mH +/-2% 0,08Ω +/-5% 12AWG OD51 H55	0,467
000-7026	Cross Coil 0,230mH +/-2% 0,08Ω +/-5% 12AWG OD52 H55	0,470
000-7027	Cross Coil 0,240mH +/-2% 0,09Ω +/-5% 12AWG OD52 H55	0,483
000-7030	Cross Coil 0,270mH +/-2% 0,09Ω +/-5% 12AWG OD54 H55	0,525
000-7031	Cross Coil 0,280mH +/-2% 0,09Ω +/-5% 12AWG OD55 H55	0,531
000-7033	Cross Coil 0,300mH +/-2% 0,09Ω +/-5% 12AWG OD55 H55	0,576
000-7035	Cross Coil 0,330mH +/-2% 0,10Ω +/-5% 12AWG OD56 H55	0,577
000-7037	Cross Coil 0,360mH +/-2% 0,11Ω +/-5% 12AWG OD57 H55	0,600
000-7040	Cross Coil 0,390mH +/-2% 0,11Ω +/-5% 12AWG OD58 H55	0,634
000-7045	Cross Coil 0,470mH +/-2% 0,12Ω +/-5% 12AWG OD61 H55	0,716
000-7048	Cross Coil 0,500mH +/-2% 0,13Ω +/-5% 12AWG OD62 H55	0,754
000-70482	Cross Coil 0,520mH +/-2% 0,13Ω +/-5% 12AWG OD62 H55	0,760
000-70484	Cross Coil 0,540mH +/-2% 0,13Ω +/-5% 12AWG OD64 H55	0,757
000-7049	Cross Coil 0,550mH +/-2% 0,13Ω +/-5% 12AWG OD64 H55	0,758
000-7050	Cross Coil 0,560mH +/-2% 0,13Ω +/-5% 12AWG OD64 H55	0,775
000-7053	Cross Coil 0,600mH +/-2% 0,14Ω +/-5% 12AWG OD65 H55	0,827
000-7055	Cross Coil 0,620mH +/-2% 0,14Ω +/-5% 12AWG OD66 H55	0,831
000-7058	Cross Coil 0,650mH +/-2% 0,14Ω +/-5% 12AWG OD67 H55	0,874
000-7060	Cross Coil 0,680mH +/-2% 0,15Ω +/-5% 12AWG OD67 H55	0,853
000-7062	Cross Coil 0,700mH +/-2% 0,15Ω +/-5% 12AWG OD68 H55	0,910
000-7063	Cross Coil 0,750mH +/-2% 0,16Ω +/-5% 12AWG OD69 H55	0,945
000-7064	Cross Coil 0,800mH +/-2% 0,16Ω +/-5% 12AWG OD70 H55	0,975
000-7065	Cross Coil 0,820mH +/-2% 0,16Ω +/-5% 12AWG OD70 H55	0,965
000-7068	Cross Coil 0,900mH +/-2% 0,17Ω +/-5% 12AWG OD72 H55	1,015
000-7068-1	Cross Coil 0,910mH +/-2% 0,17Ω +/-5% 12AWG OD72 H55	1,015
000-7070	Cross Coil 1,000mH +/-2% 0,18Ω +/-5% 12AWG OD74 H55	1,065
000-7073	Cross Coil 1,050mH +/-2% 0,19Ω +/-5% 12AWG OD75 H55	1,126
000-7075	Cross Coil 1,100mH +/-2% 0,20Ω +/-5% 12AWG OD76 H55	1,156
000-7080	Cross Coil 1,200mH +/-2% 0,21Ω +/-5% 12AWG OD77 H55	1,157
000-7083	Cross Coil 1,250mH +/-2% 0,21Ω +/-5% 12AWG OD77 H55	1,182
000-7085	Cross Coil 1,300mH +/-2% 0,22Ω +/-5% 12AWG OD79 H55	1,239
000-7087	Cross Coil 1,400mH +/-2% 0,23Ω +/-5% 12AWG OD80 H55	1,276
000-7088	Cross Coil 1,450mH +/-2% 0,24Ω +/-5% 12AWG OD82 H55	1,303
000-7090	Cross Coil 1,500mH +/-2% 0,24Ω +/-5% 12AWG OD81 H55	1,349
000-7092	Cross Coil 1,600mH +/-2% 0,24Ω +/-5% 12AWG OD83 H55	1,420
000-7094	Cross Coil 1,700mH +/-2% 0,26Ω +/-5% 12AWG OD85 H55	1,444
000-7095	Cross Coil 1,800mH +/-2% 0,26Ω +/-5% 12AWG OD86 H55	1,503
000-7098	Cross Coil 1,900mH +/-2% 0,27Ω +/-5% 12AWG OD87 H55	1,516
000-7100	Cross Coil 2,000mH +/-2% 0,28Ω +/-5% 12AWG OD88 H55	1,585
000-7103	Cross Coil 2,100mH +/-2% 0,30Ω +/-5% 12AWG OD90 H55	1,590
000-7105	Cross Coil 2,200mH +/-2% 0,30Ω +/-5% 12AWG OD91 H55	1,676
000-7106	Cross Coil 2,300mH +/-2% 0,31Ω +/-5% 12AWG OD92 H55	1,738
000-7108	Cross Coil 2,500mH +/-2% 0,32Ω +/-5% 12AWG OD94 H55	1,825
000-7110	Cross Coil 2,700mH +/-2% 0,33Ω +/-5% 12AWG OD96 H55	1,900
000-7111	Cross Coil 2,800mH +/-2% 0,34Ω +/-5% 12AWG OD97 H55	1,960

Index:	Description:	Weight (kg):
000-7112	Cross Coil 2,900mH +/-2% 0,35Ω +/-5% 12AWG OD98 H55	1,974
000-7113	Cross Coil 3,000mH +/-2% 0,36Ω +/-5% 12AWG OD99 H55	1,987
000-7114	Cross Coil 3,200mH +/-2% 0,36Ω +/-5% 12AWG OD100 H55	2,100
000-7115	Cross Coil 3,300mH +/-2% 0,37Ω +/-5% 12AWG OD102 H55	2,135
000-7117	Cross Coil 3,500mH +/-2% 0,38Ω +/-5% 12AWG OD102 H55	2,180
000-71176	Cross Coil 3,600mH +/-2% 0,39Ω +/-5% 12AWG OD104 H55	2,239
000-7118	Cross Coil 3,700mH +/-2% 0,41Ω +/-5% 12AWG OD103 H55	2,191
000-7120	Cross Coil 3,900mH +/-2% 0,42Ω +/-5% 12AWG OD106 H55	2,323
000-7121	Cross Coil 4,000mH +/-2% 0,42Ω +/-5% 12AWG OD106 H55	2,390
000-7125	Cross Coil 4,700mH +/-2% 0,47Ω +/-5% 12AWG OD113 H55	2,540
000-7128	Cross Coil 4,900mH +/-2% 0,47Ω +/-5% 12AWG OD115 H55	2,716
000-7130	Cross Coil 5,100mH +/-2% 0,49Ω +/-5% 12AWG OD115 H55	2,750
000-7135	Cross Coil 5,600mH +/-2% 0,52Ω +/-5% 12AWG OD117 H55	2,770
000-7140	Cross Coil 5,800mH +/-2% 0,52Ω +/-5% 12AWG OD121 H55	2,770
000-7198	Cross Coil 6,200mH +/-2% 0,53Ω +/-5% 12AWG OD121 H55	3,050
000-7200	Cross Coil 6,300mH +/-2% 0,55Ω +/-5% 12AWG OD121 H55	3,017
000-7202	Cross Coil 6,500mH +/-2% 0,56Ω +/-5% 12AWG OD122 H55	3,100
000-7203	Cross Coil 6,600mH +/-2% 0,56Ω +/-5% 12AWG OD123 H55	3,120
000-7205	Cross Coil 6,750mH +/-2% 0,57Ω +/-5% 12AWG OD124 H55	3,273
000-7217	Cross Coil 8,000mH +/-2% 0,62Ω +/-5% 12AWG OD129 H55	3,395
000-7219	Cross Coil 8,200mH +/-2% 0,63Ω +/-5% 12AWG OD130 H55	3,495
000-7227	Cross Coil 9,000mH +/-2% 0,64Ω +/-5% 12AWG OD135 H55	3,812
000-7237	Cross Coil 10,000mH +/-2% 0,70Ω +/-5% 12AWG OD138 H55	3,990
000-7241	Cross Coil 14,000mH +/-2% 0,87Ω +/-5% 12AWG OD152 H55	4,940
000-7242	Cross Coil 15,000mH +/-2% 0,90Ω +/-5% 12AWG OD157 H55	5,265
000-7247	Cross Coil 20,000mH +/-2% 1,07Ω +/-5% 12AWG OD169 H55	6,020
000-7258	Cross Coil 0,010mH +/-2% 0,02Ω +/-5% 14AWG OD31 H37	0,070
000-7260	Cross Coil 0,011mH +/-2% 0,02Ω +/-5% 14AWG OD31 H37	0,070
000-7269	Cross Coil 0,018mH +/-2% 0,03Ω +/-5% 14AWG OD32 H37	0,078
000-7271	Cross Coil 0,022mH +/-2% 0,03Ω +/-5% 14AWG OD33 H37	0,092
000-7273	Cross Coil 0,025mH +/-2% 0,03Ω +/-5% 14AWG OD33 H37	0,100
000-7275	Cross Coil 0,028mH +/-2% 0,04Ω +/-5% 14AWG OD37 H37	0,108
000-7276	Cross Coil 0,030mH +/-2% 0,04Ω +/-5% 14AWG OD37 H37	0,108
000-7278	Cross Coil 0,050mH +/-2% 0,05Ω +/-5% 14AWG OD37 H37	0,123
000-7280	Cross Coil 0,080mH +/-2% 0,06Ω +/-5% 14AWG OD40 H37	0,170
000-72806	Cross Coil 0,086mH +/-2% 0,06Ω +/-5% 14AWG OD41 H37	0,175
000-7281	Cross Coil 0,090mH +/-2% 0,06Ω +/-5% 14AWG OD41 H37	0,180
000-7282	Cross Coil 0,100mH +/-2% 0,07Ω +/-5% 14AWG OD41 H37	0,170
000-7283	Cross Coil 0,110mH +/-2% 0,07Ω +/-5% 14AWG OD42 H37	0,185
000-7284	Cross Coil 0,120mH +/-2% 0,08Ω +/-5% 14AWG OD43 H37	0,182
000-7293	Cross Coil 0,140mH +/-2% 0,08Ω +/-5% 14AWG OD45 H37	0,210
000-7295	Cross Coil 0,150mH +/-2% 0,09Ω +/-5% 14AWG OD45 H37	0,220
000-7296	Cross Coil 0,160mH +/-2% 0,09Ω +/-5% 14AWG OD46 H37	0,240
000-7298	Cross Coil 0,180mH +/-2% 0,10Ω +/-5% 14AWG OD47 H37	0,240
000-7300	Cross Coil 0,200mH +/-2% 0,10Ω +/-5% 14AWG OD48 H37	0,244
000-7302	Cross Coil 0,220mH +/-2% 0,11Ω +/-5% 14AWG OD49 H37	0,266
000-7304	Cross Coil 0,240mH +/-2% 0,11Ω +/-5% 14AWG OD49 H37	0,283
000-7305	Cross Coil 0,250mH +/-2% 0,11Ω +/-5% 14AWG OD50 H37	0,289
000-7306	Cross Coil 0,260mH +/-2% 0,12Ω +/-5% 14AWG OD51 H37	0,301
000-7307	Cross Coil 0,270mH +/-2% 0,12Ω +/-5% 14AWG OD51 H37	0,285
000-7314	Cross Coil 0,290mH +/-2% 0,13Ω +/-5% 14AWG OD51 H37	0,299
000-7315	Cross Coil 0,300mH +/-2% 0,12Ω +/-5% 14AWG OD52 H37	0,311
000-7320	Cross Coil 0,330mH +/-2% 0,14Ω +/-5% 14AWG OD53 H37	0,310
000-7323	Cross Coil 0,350mH +/-2% 0,14Ω +/-5% 14AWG OD54 H37	0,318
000-7328	Cross Coil 0,390mH +/-2% 0,15Ω +/-5% 14AWG OD55 H37	0,354
000-7329	Cross Coil 0,400mH +/-2% 0,15Ω +/-5% 14AWG OD55 H37	0,365
000-7330	Cross Coil 0,410mH +/-2% 0,15Ω +/-5% 14AWG OD57 H37	0,371
000-7332	Cross Coil 0,430mH +/-2% 0,16Ω +/-5% 14AWG OD57 H37	0,403
000-7338	Cross Coil 0,470mH +/-2% 0,16Ω +/-5% 14AWG OD57 H37	0,403
000-7340	Cross Coil 0,480mH +/-2% 0,17Ω +/-5% 14AWG OD58 H37	0,382
000-7342	Cross Coil 0,500mH +/-2% 0,17Ω +/-5% 14AWG OD59 H37	0,406
000-7348	Cross Coil 0,530mH +/-2% 0,17Ω +/-5% 14AWG OD59 H37	0,409
000-7352	Cross Coil 0,560mH +/-2% 0,18Ω +/-5% 14AWG OD60 H37	0,435
000-7358	Cross Coil 0,600mH +/-2% 0,18Ω +/-5% 14AWG OD61 H37	0,445
000-7360	Cross Coil 0,620mH +/-2% 0,19Ω +/-5% 14AWG OD61 H37	0,470
000-7365	Cross Coil 0,670mH +/-2% 0,21Ω +/-5% 14AWG OD63 H37	0,478
000-7366	Cross Coil 0,680mH +/-2% 0,21Ω +/-5% 14AWG OD63 H37	0,480
000-7368	Cross Coil 0,700mH +/-2% 0,21Ω +/-5% 14AWG OD63 H37	0,484
000-7370	Cross Coil 0,720mH +/-2% 0,21Ω +/-5% 14AWG OD64 H37	0,504
000-7375	Cross Coil 0,750mH +/-2% 0,22Ω +/-5% 14AWG OD65 H37	0,506
000-7384	Cross Coil 0,780mH +/-2% 0,22Ω +/-5% 14AWG OD65 H37	0,519
000-7386	Cross Coil 0,800mH +/-2% 0,22Ω +/-5% 14AWG OD66 H37	0,519
000-7388	Cross Coil 0,820mH +/-2% 0,23Ω +/-5% 14AWG OD66 H37	0,536
000-7391	Cross Coil 0,850mH +/-2% 0,23Ω +/-5% 14AWG OD67 H37	0,538
000-7395	Cross Coil 0,890mH +/-2% 0,24Ω +/-5% 14AWG OD68 H37	0,567
000-7396	Cross Coil 0,900mH +/-2% 0,24Ω +/-5% 14AWG OD68 H37	0,570

Index:	Description:	Weight (kg):
000-7397	Cross Coil 0,910mH +/-2% 0,25Ω +/-5% 14AWG OD68 H37	0,570
000-7415	Cross Coil 1,000mH +/-2% 0,27Ω +/-5% 14AWG OD69 H37	0,575
000-7420	Cross Coil 1,050mH +/-2% 0,27Ω +/-5% 14AWG OD70 H37	0,604
000-7427	Cross Coil 1,100mH +/-2% 0,27Ω +/-5% 14AWG OD71 H37	0,647
000-7437	Cross Coil 1,200mH +/-2% 0,29Ω +/-5% 14AWG OD72 H37	0,638
000-7442	Cross Coil 1,250mH +/-2% 0,29Ω +/-5% 14AWG OD73 H37	0,675
000-7443	Cross Coil 1,270mH +/-2% 0,30Ω +/-5% 14AWG OD74 H37	0,700
000-7464	Cross Coil 1,300mH +/-2% 0,30Ω +/-5% 14AWG OD74 H37	0,672
000-7465	Cross Coil 1,350mH +/-2% 0,30Ω +/-5% 14AWG OD75 H37	0,718
000-7466	Cross Coil 1,400mH +/-2% 0,31Ω +/-5% 14AWG OD75 H37	0,715
000-7467	Cross Coil 1,450mH +/-2% 0,32Ω +/-5% 14AWG OD76 H37	0,751
000-7468	Cross Coil 1,500mH +/-2% 0,34Ω +/-5% 14AWG OD77 H37	0,752
000-7470	Cross Coil 1,600mH +/-2% 0,35Ω +/-5% 14AWG OD77 H37	0,746
000-7476	Cross Coil 1,800mH +/-2% 0,37Ω +/-5% 14AWG OD80 H37	0,780
000-7482	Cross Coil 2,000mH +/-2% 0,40Ω +/-5% 14AWG OD82 H37	0,847
000-7484	Cross Coil 2,100mH +/-2% 0,40Ω +/-5% 14AWG OD84 H37	0,900
000-7486	Cross Coil 2,200mH +/-2% 0,42Ω +/-5% 14AWG OD85 H37	0,905
000-7488	Cross Coil 2,300mH +/-2% 0,44Ω +/-5% 14AWG OD86 H37	0,920
000-7493	Cross Coil 2,500mH +/-2% 0,44Ω +/-5% 14AWG OD88 H37	0,994
000-7493-5	Cross Coil 2,550mH +/-2% 0,44Ω +/-5% 14AWG OD88 H37	1,024
000-7495	Cross Coil 2,700mH +/-2% 0,46Ω +/-5% 14AWG OD91 H37	1,052
000-7502	Cross Coil 3,000mH +/-2% 0,50Ω +/-5% 14AWG OD93 H37	1,105
000-7505	Cross Coil 3,300mH +/-2% 0,51Ω +/-5% 14AWG OD96 H37	1,214
000-7512	Cross Coil 3,900mH +/-2% 0,53Ω +/-5% 14AWG OD101 H37	1,337
000-7513	Cross Coil 4,000mH +/-2% 0,60Ω +/-5% 14AWG OD101 H37	1,340
000-7522	Cross Coil 4,600mH +/-2% 0,61Ω +/-5% 14AWG OD105 H37	1,470
000-7523	Cross Coil 4,700mH +/-2% 0,62Ω +/-5% 14AWG OD106 H37	1,480
000-7527	Cross Coil 5,000mH +/-2% 0,64Ω +/-5% 14AWG OD107 H37	1,550
000-7529	Cross Coil 5,100mH +/-2% 0,65Ω +/-5% 14AWG OD108 H37	1,555
000-7534	Cross Coil 5,600mH +/-2% 0,69Ω +/-5% 14AWG OD111 H37	1,625
000-7538	Cross Coil 6,000mH +/-2% 0,76Ω +/-5% 14AWG OD114 H37	1,650
000-7542	Cross Coil 6,200mH +/-2% 0,76Ω +/-5% 14AWG OD115 H37	1,715
000-7544	Cross Coil 6,300mH +/-2% 0,76Ω +/-5% 14AWG OD115 H37	1,738
000-7546	Cross Coil 6,500mH +/-2% 0,77Ω +/-5% 14AWG OD116 H37	1,762
000-7554	Cross Coil 6,800mH +/-2% 0,77Ω +/-5% 14AWG OD118 H37	1,856
000-7556	Cross Coil 7,000mH +/-2% 0,78Ω +/-5% 14AWG OD119 H37	1,890
000-7558	Cross Coil 7,200mH +/-2% 0,79Ω +/-5% 14AWG OD120 H37	1,955
000-7562	Cross Coil 7,500mH +/-2% 0,81Ω +/-5% 14AWG OD121 H37	1,960
000-7568	Cross Coil 8,000mH +/-2% 0,87Ω +/-5% 14AWG OD122 H37	1,993
000-7570	Cross Coil 8,200mH +/-2% 0,90Ω +/-5% 14AWG OD125 H37	2,019
000-7575	Cross Coil 10,000mH +/-2% 1,05Ω +/-5% 14AWG OD129 H37	2,220
000-75752	Cross Coil 10,200mH +/-2% 1,04Ω +/-5% 14AWG OD129 H37	2,280
000-7580	Cross Coil 12,000mH +/-2% 1,10Ω +/-5% 14AWG OD136 H37	2,750
000-7590	Cross Coil 15,000mH +/-2% 1,23Ω +/-5% 14AWG OD149 H37	3,010
000-7593	Cross Coil 18,000mH +/-2% 1,43Ω +/-5% 14AWG OD155 H37	3,384
000-76064	Cross Coil 0,010mH +/-2% 0,03Ω +/-5% 16AWG OD29 H27	0,035
000-76065	Cross Coil 0,011mH +/-2% 0,03Ω +/-5% 16AWG OD30 H27	0,040
000-76068	Cross Coil 0,018mH +/-2% 0,04Ω +/-5% 16AWG OD31 H27	0,052
000-76075	Cross Coil 0,025mH +/-2% 0,05Ω +/-5% 16AWG OD33 H27	0,061
000-76077	Cross Coil 0,027mH +/-2% 0,05Ω +/-5% 16AWG OD33 H27	0,062
000-7609	Cross Coil 0,030mH +/-2% 0,05Ω +/-5% 16AWG OD33 H27	0,063
000-76103	Cross Coil 0,040mH +/-2% 0,06Ω +/-5% 16AWG OD35 H27	0,066
000-76104	Cross Coil 0,044mH +/-2% 0,06Ω +/-5% 16AWG OD35 H27	0,066
000-7611	Cross Coil 0,050mH +/-2% 0,07Ω +/-5% 16AWG OD35 H27	0,076
000-76115	Cross Coil 0,055mH +/-2% 0,07Ω +/-5% 16AWG OD36 H27	0,079
000-7615	Cross Coil 0,070mH +/-2% 0,08Ω +/-5% 16AWG OD37 H27	0,097
000-7616	Cross Coil 0,080mH +/-2% 0,09Ω +/-5% 16AWG OD39 H27	0,097
000-7618	Cross Coil 0,090mH +/-2% 0,09Ω +/-5% 16AWG OD39 H27	0,100
000-7620	Cross Coil 0,100mH +/-2% 0,10Ω +/-5% 16AWG OD40 H27	0,094
000-7621	Cross Coil 0,105mH +/-2% 0,10Ω +/-5% 16AWG OD40 H27	0,107
000-7622	Cross Coil 0,110mH +/-2% 0,10Ω +/-5% 16AWG OD41 H27	0,110
000-7623	Cross Coil 0,115mH +/-2% 0,10Ω +/-5% 16AWG OD41 H27	0,113
000-7624	Cross Coil 0,120mH +/-2% 0,11Ω +/-5% 16AWG OD42 H27	0,104
000-7626	Cross Coil 0,130mH +/-2% 0,11Ω +/-5% 16AWG OD42 H27	0,106
000-7627	Cross Coil 0,135mH +/-2% 0,11Ω +/-5% 16AWG OD42 H27	0,124
000-7628	Cross Coil 0,140mH +/-2% 0,12Ω +/-5% 16AWG OD43 H27	0,111
000-7629	Cross Coil 0,145mH +/-2% 0,12Ω +/-5% 16AWG OD43 H27	0,129
000-7630	Cross Coil 0,150mH +/-2% 0,12Ω +/-5% 16AWG OD43 H27	0,113
000-7631	Cross Coil 0,155mH +/-2% 0,12Ω +/-5% 16AWG OD43 H27	0,134
000-7632	Cross Coil 0,160mH +/-2% 0,13Ω +/-5% 16AWG OD44 H27	0,118
000-76327	Cross Coil 0,167mH +/-2% 0,13Ω +/-5% 16AWG OD45 H27	0,123
000-7634	Cross Coil 0,170mH +/-2% 0,13Ω +/-5% 16AWG OD45 H27	0,123
000-7636	Cross Coil 0,180mH +/-2% 0,13Ω +/-5% 16AWG OD45 H27	0,130
000-7638	Cross Coil 0,190mH +/-2% 0,13Ω +/-5% 16AWG OD45 H27	0,148
000-7639	Cross Coil 0,195mH +/-2% 0,13Ω +/-5% 16AWG OD45 H27	0,150
000-7640	Cross Coil 0,200mH +/-2% 0,14Ω +/-5% 16AWG OD46 H27	0,131

Index:	Description:	Weight (kg):
000-7641	Cross Coil 0,205mH +/-2% 0,14Ω +/-5% 16AWG OD46 H27	0,154
000-7642	Cross Coil 0,210mH +/-2% 0,14Ω +/-5% 16AWG OD46 H27	0,156
000-7643	Cross Coil 0,215mH +/-2% 0,14Ω +/-5% 16AWG OD46 H27	0,158
000-7644	Cross Coil 0,220mH +/-2% 0,15Ω +/-5% 16AWG OD47 H27	0,141
000-7645	Cross Coil 0,225mH +/-2% 0,15Ω +/-5% 16AWG OD47 H27	0,160
000-7646	Cross Coil 0,230mH +/-2% 0,15Ω +/-5% 16AWG OD47 H27	0,161
000-7647	Cross Coil 0,235mH +/-2% 0,15Ω +/-5% 16AWG OD47 H27	0,164
000-7648	Cross Coil 0,240mH +/-2% 0,16Ω +/-5% 16AWG OD47 H27	0,146
000-7651	Cross Coil 0,250mH +/-2% 0,16Ω +/-5% 16AWG OD48 H27	0,151
000-7654	Cross Coil 0,260mH +/-2% 0,17Ω +/-5% 16AWG OD48 H27	0,153
000-7657	Cross Coil 0,270mH +/-2% 0,17Ω +/-5% 16AWG OD48 H27	0,156
000-7660	Cross Coil 0,280mH +/-2% 0,17Ω +/-5% 16AWG OD49 H27	0,160
000-7663	Cross Coil 0,290mH +/-2% 0,17Ω +/-5% 16AWG OD49 H27	0,177
000-7666	Cross Coil 0,300mH +/-2% 0,18Ω +/-5% 16AWG OD49 H27	0,181
000-7669	Cross Coil 0,310mH +/-2% 0,18Ω +/-5% 16AWG OD50 H27	0,169
000-7672	Cross Coil 0,320mH +/-2% 0,18Ω +/-5% 16AWG OD51 H27	0,186
000-7676	Cross Coil 0,330mH +/-2% 0,19Ω +/-5% 16AWG OD51 H27	0,177
000-7679	Cross Coil 0,340mH +/-2% 0,19Ω +/-5% 16AWG OD51 H27	0,190
000-7682	Cross Coil 0,350mH +/-2% 0,20Ω +/-5% 16AWG OD51 H27	0,180
000-7685	Cross Coil 0,360mH +/-2% 0,20Ω +/-5% 16AWG OD51 H27	0,180
000-7688	Cross Coil 0,370mH +/-2% 0,20Ω +/-5% 16AWG OD52 H27	0,184
000-7691	Cross Coil 0,380mH +/-2% 0,21Ω +/-5% 16AWG OD52 H27	0,186
000-7694	Cross Coil 0,390mH +/-2% 0,21Ω +/-5% 16AWG OD52 H27	0,204
000-7697	Cross Coil 0,400mH +/-2% 0,21Ω +/-5% 16AWG OD53 H27	0,192
000-7700	Cross Coil 0,410mH +/-2% 0,22Ω +/-5% 16AWG OD53 H27	0,195
000-7703	Cross Coil 0,420mH +/-2% 0,22Ω +/-5% 16AWG OD54 H27	0,214
000-7706	Cross Coil 0,430mH +/-2% 0,22Ω +/-5% 16AWG OD54 H27	0,204
000-7707	Cross Coil 0,440mH +/-2% 0,22Ω +/-5% 16AWG OD54 H27	0,215
000-7710	Cross Coil 0,450mH +/-2% 0,22Ω +/-5% 16AWG OD55 H27	0,222
000-7715	Cross Coil 0,470mH +/-2% 0,23Ω +/-5% 16AWG OD55 H27	0,214
000-7718	Cross Coil 0,480mH +/-2% 0,24Ω +/-5% 16AWG OD55 H27	0,216
000-7721	Cross Coil 0,490mH +/-2% 0,24Ω +/-5% 16AWG OD55 H27	0,218
000-7724	Cross Coil 0,500mH +/-2% 0,24Ω +/-5% 16AWG OD56 H27	0,224
000-7726	Cross Coil 0,510mH +/-2% 0,24Ω +/-5% 16AWG OD57 H27	0,238
000-7729	Cross Coil 0,530mH +/-2% 0,25Ω +/-5% 16AWG OD57 H27	0,229
000-7733	Cross Coil 0,550mH +/-2% 0,25Ω +/-5% 16AWG OD57 H27	0,248
000-7736	Cross Coil 0,560mH +/-2% 0,25Ω +/-5% 16AWG OD57 H27	0,252
000-7739	Cross Coil 0,570mH +/-2% 0,26Ω +/-5% 16AWG OD57 H27	0,239
000-7743	Cross Coil 0,590mH +/-2% 0,27Ω +/-5% 16AWG OD58 H27	0,246
000-7746	Cross Coil 0,600mH +/-2% 0,27Ω +/-5% 16AWG OD58 H27	0,259
000-7749	Cross Coil 0,610mH +/-2% 0,27Ω +/-5% 16AWG OD58 H27	0,250
000-7752	Cross Coil 0,620mH +/-2% 0,27Ω +/-5% 16AWG OD59 H27	0,263
000-7755	Cross Coil 0,630mH +/-2% 0,27Ω +/-5% 16AWG OD59 H27	0,266
000-7760	Cross Coil 0,650mH +/-2% 0,28Ω +/-5% 16AWG OD59 H27	0,260
000-7764	Cross Coil 0,670mH +/-2% 0,28Ω +/-5% 16AWG OD60 H27	0,277
000-7766	Cross Coil 0,680mH +/-2% 0,29Ω +/-5% 16AWG OD60 H27	0,279
000-7768	Cross Coil 0,690mH +/-2% 0,29Ω +/-5% 16AWG OD60 H27	0,266
000-7770	Cross Coil 0,700mH +/-2% 0,30Ω +/-5% 16AWG OD61 H27	0,266
000-7778	Cross Coil 0,750mH +/-2% 0,30Ω +/-5% 16AWG OD62 H27	0,294
000-7788	Cross Coil 0,800mH +/-2% 0,32Ω +/-5% 16AWG OD62 H27	0,304
000-7792	Cross Coil 0,820mH +/-2% 0,32Ω +/-5% 16AWG OD62 H27	0,310
000-7795	Cross Coil 0,830mH +/-2% 0,32Ω +/-5% 16AWG OD63 H27	0,312
000-7800	Cross Coil 0,850mH +/-2% 0,33Ω +/-5% 16AWG OD63 H27	0,316
000-7801	Cross Coil 0,860mH +/-2% 0,33Ω +/-5% 16AWG OD63 H27	0,316
000-7807	Cross Coil 0,870mH +/-2% 0,33Ω +/-5% 16AWG OD63 H27	0,316
000-7809	Cross Coil 0,900mH +/-2% 0,34Ω +/-5% 16AWG OD63 H27	0,326
000-7812	Cross Coil 0,910mH +/-2% 0,34Ω +/-5% 16AWG OD65 H27	0,328
000-7815	Cross Coil 0,920mH +/-2% 0,34Ω +/-5% 16AWG OD65 H27	0,329
000-7820	Cross Coil 0,950mH +/-2% 0,35Ω +/-5% 16AWG OD66 H27	0,334
000-7825	Cross Coil 1,000mH +/-2% 0,37Ω +/-5% 16AWG OD65 H27	0,341
000-7830	Cross Coil 1,100mH +/-2% 0,38Ω +/-5% 16AWG OD68 H27	0,352
000-7835	Cross Coil 1,200mH +/-2% 0,40Ω +/-5% 16AWG OD69 H27	0,367
000-7841	Cross Coil 1,250mH +/-2% 0,40Ω +/-5% 16AWG OD70 H27	0,389
000-7844	Cross Coil 1,270mH +/-2% 0,41Ω +/-5% 16AWG OD71 H27	0,392
000-7848	Cross Coil 1,300mH +/-2% 0,42Ω +/-5% 16AWG OD71 H27	0,386
000-7852	Cross Coil 1,330mH +/-2% 0,43Ω +/-5% 16AWG OD71 H27	0,409
000-7855	Cross Coil 1,350mH +/-2% 0,44Ω +/-5% 16AWG OD72 H27	0,413
000-78558	Cross Coil 1,380mH +/-2% 0,45Ω +/-5% 16AWG OD71 H27	0,413
000-7856	Cross Coil 1,400mH +/-2% 0,45Ω +/-5% 16AWG OD72 H27	0,416
000-7860	Cross Coil 1,500mH +/-2% 0,46Ω +/-5% 16AWG OD73 H27	0,415
000-7865	Cross Coil 1,600mH +/-2% 0,49Ω +/-5% 16AWG OD74 H27	0,428
000-7868	Cross Coil 1,620mH +/-2% 0,50Ω +/-5% 16AWG OD75 H27	0,462
000-7872	Cross Coil 1,700mH +/-2% 0,51Ω +/-5% 16AWG OD76 H27	0,446
000-7875	Cross Coil 1,800mH +/-2% 0,52Ω +/-5% 16AWG OD77 H27	0,460
000-7880	Cross Coil 2,000mH +/-2% 0,53Ω +/-5% 16AWG OD79 H27	0,490
000-7883	Cross Coil 2,100mH +/-2% 0,56Ω +/-5% 16AWG OD81 H27	0,523
000-7885	Cross Coil 2,200mH +/-2% 0,56Ω +/-5% 16AWG OD81 H27	0,523

Index:	Description:	Weight (kg):
000-7888	Cross Coil 2,300mH +/-2% 0,59Ω +/-5% 16AWG OD82 H27	0,537
000-7890	Cross Coil 2,400mH +/-2% 0,60Ω +/-5% 16AWG OD83 H27	0,546
000-7895	Cross Coil 2,500mH +/-2% 0,61Ω +/-5% 16AWG OD85 H27	0,563
000-7899	Cross Coil 2,600mH +/-2% 0,63Ω +/-5% 16AWG OD85 H27	0,578
000-7900	Cross Coil 2,700mH +/-2% 0,65Ω +/-5% 16AWG OD86 H27	0,587
000-7904	Cross Coil 2,800mH +/-2% 0,66Ω +/-5% 16AWG OD86 H27	0,597
000-7906	Cross Coil 2,850mH +/-2% 0,67Ω +/-5% 16AWG OD87 H27	0,646
000-7908	Cross Coil 2,900mH +/-2% 0,65Ω +/-5% 16AWG OD89 H27	0,644
000-7910	Cross Coil 3,000mH +/-2% 0,70Ω +/-5% 16AWG OD88 H27	0,622
000-7913	Cross Coil 3,200mH +/-2% 0,73Ω +/-5% 16AWG OD90 H27	0,652
000-7915	Cross Coil 3,300mH +/-2% 0,74Ω +/-5% 16AWG OD90 H27	0,660
000-7920	Cross Coil 3,500mH +/-2% 0,76Ω +/-5% 16AWG OD92 H27	0,681
000-7924	Cross Coil 3,600mH +/-2% 0,78Ω +/-5% 16AWG OD93 H27	0,691
000-7927	Cross Coil 3,700mH +/-2% 0,80Ω +/-5% 16AWG OD93 H27	0,698
000-7930	Cross Coil 3,750mH +/-2% 0,81Ω +/-5% 16AWG OD95 H27	0,755
000-7935	Cross Coil 3,900mH +/-2% 0,82Ω +/-5% 16AWG OD95 H27	0,738
000-7940	Cross Coil 4,000mH +/-2% 0,83Ω +/-5% 16AWG OD96 H27	0,796
000-7943	Cross Coil 4,300mH +/-2% 0,86Ω +/-5% 16AWG OD97 H27	0,780
000-7945	Cross Coil 4,500mH +/-2% 0,90Ω +/-5% 16AWG OD100 H27	0,844
000-7948	Cross Coil 4,700mH +/-2% 0,90Ω +/-5% 16AWG OD99 H27	0,835
000-7953	Cross Coil 5,000mH +/-2% 0,94Ω +/-5% 16AWG OD102 H27	0,904
000-7955	Cross Coil 5,100mH +/-2% 0,95Ω +/-5% 16AWG OD102 H27	0,863
000-7961	Cross Coil 5,600mH +/-2% 1,00Ω +/-5% 16AWG OD104 H27	0,911
000-7963	Cross Coil 5,800mH +/-2% 1,04Ω +/-5% 16AWG OD105 H27	0,937
000-7965	Cross Coil 6,000mH +/-2% 1,06Ω +/-5% 16AWG OD106 H27	0,945
000-7968	Cross Coil 6,200mH +/-2% 1,07Ω +/-5% 16AWG OD107 H27	0,974
000-7971	Cross Coil 6,500mH +/-2% 1,10Ω +/-5% 16AWG OD109 H27	1,006
000-7972	Cross Coil 6,600mH +/-2% 1,10Ω +/-5% 16AWG OD111 H27	1,035
000-7974	Cross Coil 6,800mH +/-2% 1,15Ω +/-5% 16AWG OD111 H27	1,035
000-7976	Cross Coil 7,000mH +/-2% 1,16Ω +/-5% 16AWG OD113 H27	1,074
000-7977	Cross Coil 7,870mH +/-2% 1,24Ω +/-5% 16AWG OD118 H27	1,210
000-7978	Cross Coil 8,000mH +/-2% 1,27Ω +/-5% 16AWG OD116 H27	1,210
000-7980	Cross Coil 8,200mH +/-2% 1,29Ω +/-5% 16AWG OD120 H27	1,235
000-7984	Cross Coil 8,700mH +/-2% 1,42Ω +/-5% 16AWG OD120 H27	1,260
000-7985	Cross Coil 8,800mH +/-2% 1,43Ω +/-5% 16AWG OD120 H27	1,260
000-7986	Cross Coil 9,000mH +/-2% 1,45Ω +/-5% 16AWG OD122 H27	1,332
000-7988	Cross Coil 9,500mH +/-2% 1,50Ω +/-5% 16AWG OD124 H27	1,335
000-7990	Cross Coil 10,000mH +/-2% 1,54Ω +/-5% 16AWG OD126 H27	1,327
000-7992	Cross Coil 11,000mH +/-2% 1,56Ω +/-5% 16AWG OD129 H27	1,398
000-7993	Cross Coil 12,000mH +/-2% 1,71Ω +/-5% 16AWG OD131 H27	1,530
000-7994	Cross Coil 13,000mH +/-2% 1,72Ω +/-5% 16AWG OD135 H27	1,570
000-7996	Cross Coil 15,000mH +/-2% 1,88Ω +/-5% 16AWG OD147 H27	1,880
000-7998	Cross Coil 16,000mH +/-2% 1,95Ω +/-5% 16AWG OD149 H27	2,000